



► Series 5000 High Gloss Calendered Vinyl Film

Series 5000: Non-Perforated – Series 5050: Perforated

APPLICATIONS & FEATURES

- Available in 37 colors
- Easy to handle 2.8-mil (70 micron) calendered film
- Cutting and weeding performance speeds up your sign production*
- Recommended for flat and soft curved surfaces
- Gloss finish is excellent for banners, interior and exterior graphics
- Up to 6-years outdoor durability

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Colors: Gloss Meter 60° Reflection	75 to 85 Gloss Units	
THICKNESS	Micrometer, Federal Bench Type	2.8-mil (70 micron)	
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	12 lb/in width	2.1 kg/cm width
ELONGATION	Instron Tensile Tester as above	≥ 150%	
SHELF LIFE	Free from excessive moisture, temperature, direct sunlight	1 year from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	60°F to 90°F optimum	15°C to 32°C optimum
SERVICE TEMPERATURE RANGE	Film applied to etched aluminum panels 24 hours prior to testing	-40°F to 150°F	-40°C to 65°C
HUMIDITY RESISTANCE	Film applied to etched aluminum panels 24 hours prior to testing; 100% relative humidity at 100°F (38°C) for 24 hours	No appreciable effect	
GASOLINE RESISTANCE	Film applied to etched aluminum panels 24 hours prior to testing; immersed 15 minutes at 70°F (21°C); stabilized 24 hours before inspection	No appreciable effect	
DIMENSIONAL STABILITY	158°F (70°C), 48 hours	0.025 in	0.64 mm nominal
PEEL ADHESION	PSTC-1, 15 min, RT 72°F (23°C)	≥ 40 oz/in	≥ 0.45 kg/cm
LINER RELEASE	TLMI 300 in/min (762 cm/min)	150 g/2 in	30 g/cm 0.75 n/25 mm

Standard Terms & Conditions Apply




* For optimal weeding, font size must be 1 inch or greater







TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

September 2016

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA
EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands
UK:  P6 Parklands, Heywood Distribution Park, Heywood, Lancashire OL102TT, UK

 800 232 7161/+1 714 985 6300  800 329 2756
 +31 70 354 4311  +31 70 355 7721
 +44 161 884 0592  +31 70 355 7721

arlon.com